



1-800-280-0712 • (541)447-0712 • FAX (541)447-0759  
3451 SW Empire Dr • Prineville, OR 97754  
[info@btlliners.com](mailto:info@btlliners.com) • [www.btlliners.com](http://www.btlliners.com)

**Strength-Commitment-Guaranteed Containment**

## AMAR-14 MEMBRANE

<b>DESCRIPTION</b>	UV Natural Tapes Dual 24x24(1500d) COUNT PER INCH
<b>FABRICATION &amp; WAREHOUSE</b>	Prineville, OR USA
<b>WEIGHT</b>	14.1 OZ./SQ.YD. (+/-10%)      ASTM D 1910
<b>THICKNESS</b>	28 MILS (+/-10%)
<b>COATING THICKNESS</b>	Total of 8 mils
<b>TENSILE STRENGTH (GRAB METHOD)</b>	WARP 560 LBS.      ASTM D 751 WEFT 522 LBS.
<b>ELONGATION</b>	WARP 15% WEFT 18%
<b>TEAR STRENGTH (TONGUE METHOD)</b>	WARP 120 LBS/INCH      ASTM D 751 WEFT 125 LBS/INCH
<b>LOW TEMPERATURE COLD CRACK</b>	-65F      ASTM D 2136

### Standard Stock Color Tan\White

Colors available    Bottom side- White      Top side - White, Green, Tan, Red, Blue  
FR available , non stock colors are dependent on stock and availability

ALL DATA IS DRAWN FROM U.S. TESTING, PRECISION LABORATORIES AND TRI  
ENVIROMENTAL AND ARE AVAILABLE ON REQUEST.

1/11/2008