



## **BTL™-12 LINER**

**Available in  
Black/Black, Black/White, White/White  
LOW TEMPERATURE - HYDROCARBON STABLE**

<b>DESCRIPTION</b>	12 X 12 COUNT PER INCH	
<b>FABRICATION &amp; WAREHOUSE</b>	PRINEVILLE, OREGON	
<b>WEIGHT</b>	5.7 OZ./SQ.YD. (+/-5%)	ASTM D 5261
<b>THICKNESS</b>	12 MILS (+/-10%)	
<b>COATING THICKNESS</b>	1.5 MILS EACH (+/-10%)	
<b>TENSILE STRENGTH (GRAB METHOD)</b>	MD 210 LBS. CD 176 LBS.	ASTM D 751
<b>ELONGATION TO BREAK</b>	MD & CD 20%	
<b>TEAR STRENGTH (TRAPEZOIDAL METHOD)</b>	MD 65 LBS/INCH CD 55 LBS/INCH	ASTM D 4533
<b>BURSTING STRENGTH (MULLEN)</b>	350 PSI	ASTM D 751
<b>UV RESISTANCE</b>	90% STRENGTH RETAINED AFTER 2000 HRS.	ASTM G-151

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST.  
02/2015